

HEAVY DUTY REINFORCED ACRYLIC WATERPROOF COATING FOR TERRACE

Description

Dr. Fixit Newcoat is a heavy duty terrace waterproofing system, composed of specially developed highly elastic & resilient acrylic polymers, properly selected & graded fillers, lightfast & weather durable pigments, micro-fibres, additives & best quality fungicidal in water medium. It is used as a liquid applied waterproofing membrane for all types of building terraces. Dr. Fixit Newcoat is a three-layer system with coats in different colours ensuring proper build-up of the thickness, making it a reliable waterproofing system.

Areas of Application

- Building roofs / Terraces- Flat & slope.
- Over existing cementitious waterproofing treatments like brick-bat coba, concrete screeds, acrylic coatings, etc.

Features & Benefits

- **Film thickness** - Provides higher dry film thickness of 1 to 1.25 mm in three coat application.
- **Crack bridging** - Bridges cracks upto 2 mm width.
- **Application advantage** - No need to remove existing sound BB coba, Plaster, concrete surface.
- **Suitability** - Can be used for flat as well as sloping roofs.
- **Strength** - Higher tensile strength, tear resistance & bond strength with cementitious substrates.
- **Resilience** - Forms highly elastic & resilient coating so helps to withstand the structural movements.
- **Durability** - Resistant to UV & weather conditions.
- **Abrasion resistant** - No additional protective coating is required for roof subjected to foot traffic.
- **Ease of application** - Can be applied by brush & roller easily.
- **Weight addition** - Light in weight does not add extra weight over the roof.
- **Toxicity** - It is Non-toxic in nature.
- **Breathability** - It is Breathable.

Method of Application

1 SURFACE PREPARATION

- Prepare the surface thoroughly by cleaning, washing and removing dust, dirt, oil, grease and loose particles.
- Ensure that the roof slope is a minimum of 1 in 100.
- In existing old terraces such as brick-bat-coba or screeds, the substrate must be checked for its soundness. Damaged or hollow portions, sharp edges, etc. must be cut and repaired with a polymer-modified screed. Surface cracks must be filled with Dr.Fixit Crack-X or Dr.Fixit Unifiller or polymer-modified mortar in case of wider cracks.
- Bitumen based waterproofing treatments must be completely removed by mechanical scarification or by any other effective mechanical means.

2 APPLICATION

- Apply one coat of Dr. Fixit Primeseal (diluted with water in the ratio 2:1) at the rate of 10-12 m² per litre. Allow it to dry for 2-3 hours.
- Apply the first coat of Dr. Fixit Newcoat at the rate of 2 m² per litre and allow it to dry before taking up the second and third coats, the rate of application being the same.
- The sequence of colours viz-a-viz pink, green and grey can be decided depending on the desired top coat colour.
- In case only two colours are being used, ensure that the colour of the first and the third coat are the same. This would ensure correct consumption of material that will deliver a total DFT of 1 mm.

HEAVY DUTY REINFORCED ACRYLIC WATERPROOF COATING FOR TERRACE

- Drying time between coats will be 6 to 8 hours.
- Ensure that the primer and the 3 coats of Dr. Fixit Newcoat totally achieve a minimum thickness of 1 mm DFT.
- Allow the system to air cure for 7 days minimum.

Precautions & Limitations

- All corners, gaps, joints, protrusions & outlets shall be coated with two extra coats.
- Do not apply during rains; substrate MUST be in SSD condition for application of primer.
- The product is designed only for foot traffic and not vehicular or movement of machinery or equipments.
- Note : To achieve the full-proof waterproofing, parapet walls must be covered with Dr. Fixit Raincoat.

Technical Information

PROPERTIES	SPECIFICATION	RESULTS
Solid Content, %	TGA/DTA Analyser	69
Polymer Content, %	TGA/DTA Analyser	35
Hardness (Shore A)	ASTM D 2240: 2002	80
Tensile Strength, N/mm ²	ASTM D 412 : 2002	2.6
Elongation at Break, %	ASTM D 412 : 2002	200
UV Resistant - Accelerated Weathering (2000 hours)	ASTM G 154 : 2000	Excellent: No thermal degradation, Cracking, chalking and discoloration
Adhesion Strength, N/mm ²	ASTM D 4541 : 2002	0.9
Water Vapour Transmission	ASTM E 96 : 2000	19 g/m ² /day
Algae & Fungus Resistant	SS 345 : 1998	No algae & fungus Growth
Crack Bridging	ASTM C 836: 1995 (Adopted)	a) No cracks up to 2 mm width b) No cracks up to 1 mm (10 cycles)
Rapid chloride permeability	ASTM C 1202 - 97	Very low
Water permeability (Depth of penetration at 5 bar pressure)	BS EN 12390, part 8 :2000	6

Coverage

2 m² per litre per coat

Packaging

4 & 20 litres

Shelf Life & Storage

- Shelf life is 12 months from the date of manufacturing in unopened condition.
- Store in a cool & dry place.

Dr. Fixit Newcoat



HEAVY DUTY REINFORCED ACRYLIC WATERPROOF COATING FOR TERRACE

Health & Safety Precautions

- Skin Contact: Wash skin with soap & water. Remove contaminated clothes.
- On eye contact: Immediately splash eyes with plenty of water. Consult Physician if irritation persists.
- Ingestion: Do not induce vomiting. Never give anything by mouth to an unconscious person. Call a Physician.

Other Product Categories Available

DR. FIXIT has wide range of Waterproofing & Construction chemicals which includes,

- Waterproofing Products
- Repair Products
- Sealants
- Flooring Products
- Exterior Coating Products
- Tile Fixing Range
- Concrete Admixtures
- Grouts



Pidilite Industries Limited

Construction Chemicals Division
Ramkrishna Mandir Road
Post Box No. 17411
Andheri (E) Mumbai 400059 INDIA
Tel +91-22-2835 7000 • Fax +91-22-2835 7008
website www.doctor-fixit.com • E-mail drfixit@pidilite.com
Toll Free No.: 1800-22-5502

DISCLAIMER The product information & application details given by the company & its agents has been provided in good faith & meant to serve only as a general guideline during usage. Users are advised to carry out tests & take trials to ensure on the suitability of products meeting their requirement prior to full scale usage of our products. Since the correct identification of the problems, quality of other materials used and the on-site workmanship are factors beyond our control, there are no expressed or implied guarantee / warranty as to the results obtained. The company does not assume any liability or consequential damage for unsatisfactory results, arising from the use of our products.