

Dr. Fixit Epoxy Injection Grout



TWO PART EPOXY BASED MOISTURE INSENSITIVE INJECTION GROUT

Description

Dr. Fixit Epoxy Injection Grout is a solvent less crack injection material composed of very low viscous liquid epoxy resin & amine hardener system. It is used to seal & inject cracks in concrete floors, walls & structures because it provides deep penetration, shrink free solid mass, strong bonding inside the cracks and excellent resistance to honey combing & chemicals.

Standard Compliance / Specification

- Meets the requirement of BS 6319 & ASTM C 881 standards.

Areas of Application

- Permanent bonding solution for concrete cracks.
- Repair of crack concrete areas in floors, walls, tanks & sea walls.
- Injection in to cracks & honey combing in concrete & masonry.

Features & Benefits

- **Speciality** - Specially formulated for Middle East climatic conditions.
- **Bonding** - Seals & bonds strongly with cracks of concrete, floors & walls and provides smooth working surface & avoids damage of the concrete substrate.
- **Penetration** - Low viscosity helps in deep penetration into the cracks. Thus seals the cracks permanently.
- **Repairs** - Because of low viscosity, strong bonding, higher strength development than parent concrete, shrink free nature & waterproofing characteristics, makes it suitable for repairs of heavy concrete structures like bridges, dams, buildings, etc.
- **Resistant** - Resistance to aggressive chemicals, corrosion, abrasion & dust formation.
- **Moisture Insensitive** - Excellent adhesion to cement substrates even under salt water & moisture.

Method of Application

1 SURFACE PREPARATION

- Surface must be strong, dry, clean & free from dust, oil, grease, curing compounds, coatings & other loose materials. For better performance sand blasting, high pressure water jet cleaning, hydrochloric acid etching, mechanical grinding (by pneumatic tools) & wire brushing may be done. In case of acid etching, wash the surface till neutralization.
- open the cracks & clean by blow of oil free air to ensure complete removal of dust & loose particles.

2 PLACING / FIXING OF NOZZLES

- Drill holes into the crack of diameter higher than the grouting nipples upto a depth of at least 1/3rd of structural member.
- Insert injection nipples / nozzles in to the drill holes at the intervals along the length of etch crack. The distance between each nipple will depend on width & depth of crack. spacing should be close enough to ensure that the resin penetrates along the cracks till the next point of injection.
- The surface of the cracks in between the nipples should be sealed with Dr. Fixit concrete Repair mortars about 30-40 mm wide & 2-3 mm thick band. In case the crack is through & through of a wall or slab, cracks at both the sides must be sealed in similar fashion. First fix the nozzles in the front portion crack, then fix the nozzles at midway points of the front nozzles. This ensures complete filling of grout into crack & surrounding areas.
- The repaired work shall be allowed to cure for atleast 8 hrs at 35°C, at low temperature of 5-12°C curing time is extended and the applicator must ensure that the surface sealant has adequately cured prior to continuing the work.
- One end of the injection hose shall be attached to the lowest nipple on vertical cracks or to either end of the horizontal cracks. Alternative methods of resin injection are currently in use, they include the system where injection nipples are bonded to the substrate.

Dr. Fixit Epoxy Injection Grout



TWO PART EPOXY BASED MOISTURE INSENSITIVE INJECTION GROUT

3 MIXING

- Thoroughly mix the entire hardener and base resin contents until the liquids become clear.

4 INJECTION

- Dr. Fixit Epoxy Injection Grout should be used with standard injection equipment having closed containers. The injection pressure should be at least 0.2 n/mm² (2 bar).
- Only mix sufficient resin that can be used within the pot life of the materials.
- After completion of the injection work, the injection system shall be allowed to cure for 24 hours and shall be left undisturbed for this time

Precautions & Limitations

- Use the material within the pot life expiry period.
- Mix entire pack quantity.
- Do not dilute the material with solvents to reduce the viscosity.
- Ensure that nozzles are fixed properly without any air leakage.

Technical Information

PROPERTIES	SPECIFICATION	RESULTS
Pot life @ 20°C & 65% RH, minutes		60-65
Pot life @ 30°C & 65% RH, minutes		40-45
Pot life @ 40°C & 65% RH, minutes		20-35
Sp. Gravity @ 20°C		1.02
Initial setting time, Hrs		6
Compressive strength, N/mm ²	BS:6319 : part 2	40 - 1 day 70 - 7 days
Flexural strength, N/mm ²	BS:6319 : part 3	45 - 7 days
Tensile strength, N/mm ²	BS:6319 : part 7	17 - 7 days
Water permeability, %		Nil
Bond strength, kN	ASTM : C 881	Concrete Failure
Viscosity on brookefield RVT Model @ 30°C, CPS		200 - 400

PACKING

1 & 3 Kg

Coverage

Fresh mix density 1.02 - 1.06 kg/ ltr.

Dr. Fixit Epoxy Injection Grout



TWO PART EPOXY BASED MOISTURE INSENSITIVE
INJECTION GROUT

Shelf Life & Storage

- Shelf life is 12 months from the date of manufacturing in unopened condition. store in a cool & dry place. keep away from direct sun light.

Health & Safety Precautions

- As with all chemical products, caution should always be exercised. Protective clothings, such as gloves and goggles, should be worn.
- Treat any contact to the skin or eyes with fresh water immediately. should any of the products be accidentally swallowed, do not induce vomiting but call for medical assistance immediately.
- Ensure the pack is available for the medical attendant to examine any relevant instructions and contents details.
- Reseal all containers after use and ensure product is stored as instructed.
- Do not smoke when handling this product.
- Wear protective gloves and goggles when handling the application of this product.
- Do not inhale.
- Store away from sunlight.

Other Product Categories Available

DR. FIXIT has wide range of Waterproofing & Construction chemicals which includes,

- Waterproofing Products
- Repair Products
- Sealants
- Flooring Products
- Exterior Coating Products
- Tile Fixing Range
- Concrete Admixtures
- Grouts



Pidilite Industries Limited

Construction Chemicals Division
Ramkrishna Mandir Road
Post Box No. 17411
Andheri (E) Mumbai 400059 INDIA
Tel +91-22-2835 7000 • Fax +91-22-2835 7008
website www.doctor-fixit.com • E-mail drfixit@pidilite.com
Toll Free No.: 1800-22-5502

DISCLAIMER The product information & application details given by the company & its agents has been provided in good faith & meant to serve only as a general guideline during usage. Users are advised to carry out tests & take trials to ensure on the suitability of products meeting their requirement prior to full scale usage of our products. Since the correct identification of the problems, quality of other materials used and the on-site workmanship are factors beyond our control, there are no expressed or implied guarantee / warranty as to the results obtained. The company does not assume any liability or consequential damage for unsatisfactory results, arising from the use of our products.