

# Dr. Fixit Micro Concrete



## FLOWABLE MORTAR FOR REPAIRS OF DAMAGED REINFORCED CONCRETE MEMBERS

### Description

**Dr. Fixit Micro Concrete** is a ready to use dry powder which requires only addition of clean water at site to produce a free flowing non shrink repair micro concrete. It is composed of good quality cement, properly selected aggregates & additives. It is used & designed for repairing of damaged reinforced concrete elements like columns, beams & structure where the areas are restricted or not easily accessible for proper placement of concrete using vibrator. Dr. Fixit Micro Concrete has excellent flowability, workability & proper particle size to reach small & congested reinforcement.

### Specification

**Dr. Fixit Micro Concrete** meets the requirement of ASTM C 109: 99, ASTM C 307, BS 1881 Part 207

### Areas of Application

- Repair of damaged reinforced concrete elements like beams, columns, wall, etc. where access is restricted and compaction is not possible.
- For Jacketing of RCC columns to increase load-taking capacity (strengthening of a vertical members)

### Features & Benefits

- Pumpable - Can be pumped or poured into restricted locations.
- Flowable - Flowable mortar hence does not require compaction.
- Shrinkage compensation - Controlled expansion system which compensates for shrinkage and settlement in the plastic state.
- Strength - Develops high initial and ultimate compressive strength.
- Moisture resistant - Offers excellent resistance to moisture ingress.
- Durability - Makes repaired sections highly durable & compatible to parent concrete.
- Thickness build up - Can be applied at 100 mm thickness at one stroke
- Chloride content - Contains no chloride based additive so prevents corrosion of reinforcement.
- Early reinstatement -Rapid strength gain helps in early reinstatement & removal of shuttering.

### Method of Application

#### 1 SURFACE PREPARATION

- Clean the surface and remove loose concrete, dust, oil, paint, grease, waterproof coating, etc.
- Expose fully any corroded steel in the repair area and remove all scale and corrosion deposits. Light shot blasting is highly recommended. Apply Dr. Fixit Rust Remover for rust free bars.
- Apply Dr. Fixit Epoxy Zinc Primer over the cleaned re-bars and allow it to dry before pouring of Dr.Fixit Micro Concrete.
- Saturate the substrate with water to prevent absorption of water from the mixed material.
- For a dry substrate, it should be primed by applying one coat of Dr. Fixit Epoxy Bonding Agent. Allow the bonding agent to reach tacky condition before pouring of mix concrete.

#### 2 MIXING

- Use PAN Mixer for mixing of Dr. Fixit Micro Concrete.
- Charge 85-90 % of clean & potable mixing water (3.75 to 4 liters per 25 kg bag) to a PAN Mixer.
- Start addition of Micro Concrete powder slowly under continuous mixing. Keep mixing for 2 minutes. Add balance quantity 15 - 20% of mixing water & again mix for another 2-3 minutes to form a homogeneous, free flowing, uniform & lump-free mix.

# Dr. Fixit Micro Concrete



## FLOWABLE MORTAR FOR REPAIRS OF DAMAGED REINFORCED CONCRETE MEMBERS

### 3 APPLICATION

- Pour or pump the mixed Dr. Fixit Micro Concrete into a watertight shuttering.
- Cure the repaired concrete for minimum 7 days before removing the shuttering or alternatively use Dr. Fixit Curing Compound for curing.

### Precautions & Limitations

- Dr. Fixit Micro Concrete can applied in section upto 100 mm depth.
- For thickness more than 100 mm, addition of pre-calculated aggregates may be required. Consult technical team for more details.
- Strictly follow water-powder ratio as specified.
- Ensure that the shuttering is 100% watertight.
- Ensure full exposure of reinforced steel.
- Consult structural engineer if the diameter of rebar is reduced by more than 20% than the original diameter.
- Replacement or provision of additional steel shall be done in consultation with structural consultant.

### Technical Information

PROPERTIES	SPECIFICATION	RESULTS
Compressive strength	ASTM C 109 : 99	20 N/mm <sup>2</sup> at 10 day 40 N/mm <sup>2</sup> at 30 days 62 N/mm <sup>2</sup> at 40 days 70 N/mm <sup>2</sup> at 50 days
Flexural Strength	ASTM C 580	11 N/mm <sup>2</sup> at 5 days
Tensile Strength	ASTM C 307	6 N/mm <sup>2</sup> at 7 days
Pull Off (Bond) strength	BS 1881, Part 207	1.6 - 1.8
Carbonation resistant	:	Passes the Accelerated carbonation test
Water absorption after 24 hrs (%)		0.45
Chloride content		Nil

### PACKING

25 kg

### Coverage

1.3 m<sup>2</sup> per 25 kg pack at 10 mm thickness  
Yield - 13.5 ltrs

### Shelf Life & Storage

Shelf life is six months from the date of manufacturing. Store at cool & dry place in unopened condition.

### Health & Safety Precautions

- As with all chemical products, caution should always be exercised.
- Protective clothings such as gloves and goggles should be worn (see packaging for specific instructions).
- Treat any contact to the skin or eyes with fresh water immediately.
- Should any of the products be accidentally swallowed, do not induce vomiting but call for medical assistance immediately.

# Dr. Fixit Micro Concrete



FLOWABLE MORTAR FOR REPAIRS OF DAMAGED REINFORCED CONCRETE MEMBERS

## Other Product Categories Available

DR. FIXIT has wide range of Waterproofing & Construction chemicals which includes,

- Waterproofing Products
- Repair Products
- Sealants
- Flooring Products
- Exterior Coating Products
- Tile Fixing Range
- Concrete Admixtures
- Grouts



### Pidilite Industries Limited

Construction Chemicals Division  
Ramkrishna Mandir Road  
Post Box No. 17411  
Andheri (E) Mumbai 400059 INDIA  
Tel +91-22-2835 7000 • Fax +91-22-2835 7008  
website [www.doctor-fixit.com](http://www.doctor-fixit.com) • E-mail [drfixit@pidilite.com](mailto:drfixit@pidilite.com)  
**Toll Free No.: 1800-22-5502**

**DISCLAIMER** The product information & application details given by the company & its agents has been provided in good faith & meant to serve only as a general guideline during usage. Users are advised to carry out tests & take trials to ensure on the suitability of products meeting their requirement prior to full scale usage of our products. Since the correct identification of the problems, quality of other materials used and the on-site workmanship are factors beyond our control, there are no expressed or implied guarantee / warranty as to the results obtained. The company does not assume any liability or consequential damage for unsatisfactory results, arising from the use of our products.