



Dr. Fixit Epoxy Zinc Primer

FOR CATHODIC PROTECTION TO RE-BARS
& STEEL SURFACES

Description

Dr. Fixit Epoxy Zinc Primer is a two-component system based on metallic Zinc and epoxy resin, hardener & additives which on mixing gives a grey coloured liquid. **Dr. Fixit Epoxy Zinc Primer** is recommended for coating on steel reinforcement or steel surfaces as an anti corrosion primer. The product actively resists corrosion within the confines of the repair location and avoids the generation of incipient anodes in immediately adjacent locations.

Areas of Application

For coating of re-bars and steel surfaces.

Features & Benefits

- **Passivation** - Active zinc-rich system combats corrosion by electro chemicals means.
- **Ease of application** - Easy to mix & applicable by brush or spray.
- **Time saving** - Saves time because it dries quickly (touch dry time 15 to 45 minutes).
- **Compatibility** - Excellent compatibility and suitable primer for steel surfaces and can be over coated by epoxy or polyurethane coatings.
- **Bonding** - Bonds strongly to cement concrete & mortars.
- **Chemical resistance** - Resistance to commonly used acids & alkali.

Method of Application

1 SURFACE PREPARATION

- Expose fully any corroded steel in the repair area and remove all loose scale and corrosion deposits. Care should be taken to clean the back side of exposed steel bars as well. Grit blasting is recommended for this purpose.
- The application of **Dr. Fixit Epoxy Zinc Primer** must take place immediately on a dry steel surface after completion of the preparation work and not later than three hours.

2 APPLICATION

- Apply first coat of **Dr. Fixit Epoxy Zinc Primer** using a suitable brush, making sure that the back of exposed steel reinforcement bars are properly covered.
- Apply second coat, in case of any discontinuity in the first coat, after drying of first coat for minimum 1 hour.
- The primed surface should not be left exposed for a longer time. The application of concrete repair material should proceed as soon as the **Dr. Fixit Epoxy Zinc Primer** is fully dried.

Precautions & Limitations

- **Dr. Fixit Epoxy Zinc Primer** should not be applied when the temperature is below 10°C & is above 40°C.
- It is flammable so prevent from naked flame.
- Keep away from source of ignition.
- In case needed, fire extinguish with CO₂ or foam extinguisher.



Dr. Fixit Epoxy Zinc Primer

FOR CATHODIC PROTECTION TO RE-BARS
& STEEL SURFACES

Technical Information

PROPERTIES	RESULTS
Pot life of mixed material @30°C, minutes	150
Specific gravity, g/cc	2.1 +/-0.1
Thickness of application (W.F.T), microns	70 - 75
Inter coat time @30°C, Hour	1
Flash point, °C	16

PACKING

1 ltr

Coverage

Coverage rate will be 6 m² / ltr at DFT of 100 microns

Health & Safety Precautions

- Like for all chemical products, caution should always be exercised. Protective clothings such as gloves and goggles should be worn.
- Treat any contact to the skin or eyes with fresh water immediately.
- Should the product be accidentally swallowed, do not induce vomiting but call for medical assistance immediately.

Other Product Categories Available

DR. FIXIT has wide range of Waterproofing & Construction chemicals which includes,

- Waterproofing Products
- Repair Products
- Sealants
- Flooring Products
- Exterior Coating Products
- Tile Fixing Range
- Concrete Admixtures
- Grouts



Pidilite Industries Limited

Construction Chemicals Division
Ramkrishna Mandir Road
Post Box No. 17411
Andheri (E) Mumbai 400059 INDIA
Tel +91-22-2835 7000 • Fax +91-22-2835 7008
website www.doctor-fixit.com • E-mail drfixit@pidilite.com
Toll Free No.: 1800-22-5502

DISCLAIMER The product information & application details given by the company & its agents has been provided in good faith & meant to serve only as a general guideline during usage. Users are advised to carry out tests & take trials to ensure on the suitability of products meeting their requirement prior to full scale usage of our products. Since the correct identification of the problems, quality of other materials used and the on-site workmanship are factors beyond our control, there are no expressed or implied guarantee / warranty as to the results obtained. The company does not assume any liability or consequential damage for unsatisfactory results, arising from the use of our products.