

# Dr. Fixit Epoxy Bonding Agent



TWO-PART SOLVENT FREE EPOXY RESIN BASED  
BONDING AGENT

## Description

**Dr. Fixit Epoxy Bonding Agent** is a two part solvent free bonding agent composed of liquid epoxy resin and hardener. It is used for bonding of structural concrete new to old concrete and bonding agent for bricks and steel components because it gives excellent bonding properties to freshly mixed concrete/mortars, glazed bricks, tiles, etc.

## Areas of Application

- Bonding agent for bonding of old to new concrete / mortar.
- To extend or repair structural concrete.
- Bonding agent of glazed brick, tiles, steel & structural members.

## Features & Benefits

- **Ease of application** - Easily applicable by brush as a bonding agent for old to new concrete / mortar.
- **Adhesion** - Excellent adhesion to almost all building materials.
- **Strength** - Bond strength exceeds the tensile strength of concrete hence no failure of concrete due to high degree of movements.
- **Open time** - Comfortable open time to complete the work easily.
- **Shrinkage** - Very low shrinkage as compared to polymer modified cementitious bonding agents
- **Water resistance** - Excellent water resistance and sealing property prevents leakage.
- **Toxicity** - Nontoxic.
- **Moisture tolerant** - It is moisture tolerant hence provides strong bond of new concrete to fresh concrete.
- **Durability** - Very high durable bond.
- **Chemical Resistance** - Resistant to chemical attack.

## Method of Application

### 1 SURFACE PREPARATION

- The surface must be thoroughly cleaned and prepared. Remove all loose particles, dirt, dust, laitance, and mould release agents, curing compounds, oils, grease, floor hardeners and any waterproofing materials for best results.
- Remove laitance, dirt and dust by mechanical scarification such as wire brushing, scrapping, scabbling or grit blasting.
- Clean the dust by pressurized air or by washing with water.
- Oil and grease should be removed by degreasing with solvents like turpentine or thinners.
- Visible signs of mould growth should be removed & treated with a fungicidal solutions
- New concrete must be cured completely .

### 2 MIXING

- Stir the material of both base & hardener containers to a uniform colour & consistency.
- Transfer the entire quantity of base component into a clean & dry vessel, then poured entire quantity of hardener into the base. The two parts must be mixed thoroughly with a low speed mixer (150 to 200 rpm for about 3 to 4 minutes) to get uniform colour & consistency of the mixed material.



# Dr. Fixit Epoxy Bonding Agent

TWO-PART SOLVENT FREE EPOXY RESIN BASED BONDING AGENT

### 3 APPLICATION

- Mixed material should be brushed applied on the prepared surface.
- Overlay of concrete / mortar has to be placed on Dr. Fixit Epoxy Bonding Agent when it is tacky.
- In case Dr. Fixit Epoxy Bonding Agent has dried, apply a 2nd coat before placing the concrete / mortar.

### Precautions & Limitations

- Dr. Fixit Epoxy Bonding Agent should be applied on old concrete surface.
- Before Dr. Fixit Epoxy Bonding Agent get tack free, apply new concrete or mortar.
- If applied coating gets fully dry then apply 2nd coat over it.

### Technical Information

PROPERTIES	SPECIFICATION	RESULTS
Appearance of mix		Viscous brushable liquid
Colour		Grey
Pot Life @ 30°C, hrs		1
Tack free time @30°C, hrs		1-2
Shear Bond strength, N/sqmm	ASTM C : 881	Concrete failure
Tensile strength, 7days - N/sqmm		20
Cure time, days		7
Mixing ratio, B : H parts by weight		100 : 87
Application Temp. °C		15 - 35

### PACKING

1 kg

### Shelf Life & Storage

- Shelf life is 12 months from date of manufacturing in unopened containers.
- Store at cool & dry place, away from sun heat .

### Coverage

- 2 - 3 sq meter / Kg depending on the substrate.

### Health & Safety Precautions

- As with all chemical products, caution should always be exercised. Protective clothing's, such as gloves and Goggles should be worn.
- Treat any contact to the skin or eyes with fresh water immediately. Should any of the products be accidentally swallowed, do not induce vomiting but call for medical assistance immediately.
- Ensure the pack is available for the medical attendant to examine any relevant instructions and contents details.
- Reseal all containers after use and ensure product is stored as instructed.
- Do not smoke when handling this product.
- Do not inhale.
- Apply in well-ventilated areas.
- Apply away from naked flames.
- Store away from sunlight.



# Dr. Fixit Epoxy Bonding Agent

TWO-PART SOLVENT FREE EPOXY RESIN BASED  
BONDING AGENT

## Other Product Categories Available

Dr. Fixit has wide range of Waterproofing & Construction chemicals which includes,

- Waterproofing Products
- Repair Products
- Sealants
- Flooring Products
- Exterior Coating Products
- Tile Fixing Range
- Concrete Admixtures
- Grouts



### Pidilite Industries Limited

Construction Chemicals Division  
Ramkrishna Mandir Road  
Post Box No. 17411  
Andheri (E) Mumbai 400059 INDIA  
Tel +91-22-2835 7000 • Fax +91-22-2835 7008  
website [www.doctor-fixit.com](http://www.doctor-fixit.com) • E-mail [drfixit@pidilite.com](mailto:drfixit@pidilite.com)  
**Toll Free No.: 1800-22-5502**

**DISCLAIMER** The product information & application details given by the company & its agents has been provided in good faith & meant to serve only as a general guideline during usage. Users are advised to carry out tests & take trials to ensure on the suitability of products meeting their requirement prior to full scale usage of our products. Since the correct identification of the problems, quality of other materials used and the on-site workmanship are factors beyond our control, there are no expressed or implied guarantee / warranty as to the results obtained. The company does not assume any liability or consequential damage for unsatisfactory results, arising from the use of our products.