



WATERPROOFING SOLUTIONS

DR. FIXIT FEVIMATE XL

High performance Tile Fixing Adhesive for internal wall/ floor & external Flooring & Tile-on-Tile Applications

Dr. Fixit Fevimate XL is a blended polymer modified cement based powder tile adhesive. It gives excellent bond on cementitious surfaces like, concrete, plaster, etc. **Dr. Fixit Fevimate XL** forms a waterproof barrier between two surfaces and has excellent 'grab' properties

AREA OF APPLICATION:

For fixing all types of tiles on internal wall / floor, external floor & tile on tile applications. As well as swimming pool tiling applications

FEATURES & BENEFITS:

- Ready to use, needs only mixing with water
- Excellent adhesion, low shrinkage
- Suitable for indoor and tile on tile applications
- Sufficiently flexible to accommodate physical & thermal movements
- Needs no curing, needs no hacking or mechanical key on the surfaces
- Floors can be used after 24 hours
- Curing not required
- Soaking of tiles & backing of surface not required

METHOD OF APPLICATION:

- The surface to be tiled should be clean and sound. Old surfaces must be free from wax, grease, polish, etc.
- The surface to be tiled should be sound and thoroughly cleaned. Old surface should be free from wax, grease, polish etc.
- Pour one 25 kg. Bag in approx. 8 lt. of clean water (recommended proportion approx. 3:1 of powder to water by volume). At site, addition of water shall be adjusted to attain desired consistency. Do not put water into the powder. Mix with a trowel / slow speed drills (50 - 100 rpm) until a lump free homogeneous paste is obtained.
- Always mix the required quantity, which can be consumed within the prescribed pot life adopting the mixing proportion mentioned above.
- Spread the adhesive to a thickness of approx. 3-6 mm and comb with a notched trowel. Strictly apply the adhesive paste which can be tiled with in 10 to 15 mins.
- Intermittently touch the adhesive paste on substrate by finger. If the adhesive sticks to fingers then continue tiling and if not scrape off the adhesive and apply new coat.
- Start placing the tiles on the surface to be tiled. Tap the tiles properly to ensure complete coverage of the backside of tiles and to eliminate the possibility of any air voids.
- Keep joints between two-tiles using spacers that are available with **Dr. Fixit Fevimate XL** bag.
- Allow tiling to set for 24 hours and start filling joints next day with **ROFF RAINBOW TILE MATE**.
- Use mechanical clamps for holding the heavy stones in positions on vertical surface.
- **Dr. Fixit Fevimate XL** also can be applied at 3-mm thickness for fixing of normal tiles in toilets and swimming pool area.
- Mix **ROFF RAINBOW TILE MATE** powder with water in ratio 2.5: 1 (1 water to 2.5 **ROFF RAINBOW TILE MATE**) and press it firmly in joints.
- After grouting clean and polish tiles with a damp sponge or cloth.

PRECAUTIONS & LIMITATIONS:

- Do not use for vertical cladding of heavy tiles
- Always add powder to water and not water to powder
- Do not add more water than recommended
- Do not add sand or cement at site
- Before doing tile-on-tile application, ensure that the original tiling surface is in sound condition.
- In case of undulations in the existing floor, rectify the same before applying **Dr. Fixit Fevimate XL**
- **Strictly not recommended for the direct use on gypsum plaster, paint, wood & metal. For such applications apply Dr. Fixit Pidicrete MPB over a dry & clean surface. Thereafter within 60 mins start applying Dr. Fixit Fevimate TL paste. Particularly for application over wood/metal the surface must be sufficiently rigid & stable to receive tile and capable of carrying the load of tiles without excessive deflection. Consult Dr. Fixit.**

TECHNICAL INFORMATION:

- Appearance : Cement Grey Powder
- Mix ratio : Approx. 3 : 1 (by vol).
- Open time : Approx. 10 - 15 minutes at 30°C
- Pot life : approx. 2 hrs at 30°C
- Coverage : 60 - 70 sqft/25Kg. Bag at 3 mm thickness
- : 30 - 35 sqft/25Kg bag at 6 mm thickness
- Trafficable time : 24 hrs (max.)
- Curing time : 14 days at 30°C

PACKING: 5 kg, 20 kg, 25 kg & 50 kg

Pidilite Industries Limited

Construction Chemicals Division

Ramkrishna Mandir Road Post Box No. 17411

Andheri (E) Mumbai 400059 INDIA

Tel +91-22-2835 7000 Fax +91-22-2835 7008

website www.doctor-fixit.com E-mail drfixit@pidilite.com

Disclaimer:

The product information & application details given by the company & its agents has been provided in good faith & meant to serve only as a general guideline during usage. Users are advised to carry out tests & take trials to ensure on the suitability of products meeting their requirement prior to full scale usage of our products. Since the correct identification of the problems, quality of other materials used and on-site workmanship are factors beyond our control, there are no expressed or implied guarantee / warranty as to the results obtained. The Company does not assume any liability or any consequential damage for unsatisfactory results, arising from the use of our products.